

# Akrylfog Flex 10%

## Acrylic sealant

### Product description:

Acrylic based latex/decorator caulk for narrower joints and cracks without demands on great elasticity or high uptake of movement.

### Applications:

For use in dry frost-free environments. Easy-to-work, water soluble before hardening.

### Technical data:

Type	Acrylic sealant
Curing system	Evaporation of water
Consistency	Thixotropic
Density [kg/dm <sup>3</sup> ]	1,6
Color	WHITE
Packaging [ml]	300, 600
Paintable*	Yes
Solids content	83%
Skin time/open time [min]	~15 min
Shore A	~25
Application temperature (wet) [C°]	+5 ÷ +40 (Best result: +20°C)
Application temperature (cured) [C°]	-50 ÷ +90
Application temperature (cured, short time span) [C°]	-65 ÷ +130
Shelf life cool & dry [months]**	24
Storage temperature [°C]	+5 - +25

All values at 23 ° / 50 % RH, unless otherwise indicated

\* "Paintable" listed only as yes or no in the table. ESSVE always recommend testing before full-scale implementation. Always bear in mind that all product combinations has not been tested and therefore it is always up to the customer/end user to check that the paint, varnish or other coating is compatible with the product in question.

\*\* Best before labeled packaging for products with bag in box applies to unopened bag.

### Instruction/Application:

Follow the directions on the package. Ambient and material temperature should be 5°C ÷ +40°C, the best results are obtained at +20°C. The

cartridge should be at room temperature. Make sure that the surfaces are dry, clean, free from dust/particles and grease/oil before applying the sealant. If necessary, clean thoroughly. Use alcohol, acetone or other

leaves no residues. Nafta can leave a layer of oil that can give adhesion problems. Place a backer rod (ex. ESSVE

Backing Rod) in the bottom of the joint at the correct depth. To avoid damage to the backer rod place it with blunt and smooth tool. A damaged backing rod can cause air bubbles in the joint. The sealant should be applied by sealant dispenser gun and pressed into the seam in such a way that the material is in full contact with the surfaces. After application smooth out the sealant with a smoothing tool dipped in soapy water. Make sure that water does not come between the joint side and the compound.

#### **Resistance to aging:**

Good, the product is highly resistant to ozone and UV radiation.

#### **Cleaning:**

Wet product can be cleaned with water and a rag. Cured product can only be removed mechanically.

#### **Storage:**

Best stored dark, cool and dry. The product can withstand temperatures down to -10 °C for short periods, but should not be exposed to freezing temperatures for a longer time. Store upright.

#### **Safety:**

See separate safety data sheet.

#### **Notes:**

*All information in this document is given in accordance with known facts and information at the time of writing. The information is subject to change without further notification. The document is updated continuously in conjunction with regular revision or in the event of major-specific technical changes.*

*All advice given by ESSVE should only be seen as indicative and does not mean that ESSVE can be held responsible for the advice provided. It is always the customer's responsibility, at his/her own risk, to decide on the choice of product, usage, applications, etc. The Supplier's advice is only a part of the customer's decision making data.*